

LAW OFFICES
SUGHRUE, MION, ZINN, MACPEAK & SEAS, PLLC
 2100 PENNSYLVANIA AVENUE, N.W.
 WASHINGTON, DC 20037-3213
 TELEPHONE (202) 293-7060
 FACSIMILE (202) 293-7860
 www.sughrue.com

December 12, 2000

BOX PCT

Assistant Commissioner for Patents
 Washington, D.C. 20231

PCT/JP98/02610
 -filed June 12, 1998

Re: Application of Shiro KAMIYAMA, Katsumi KOHAMA, Hiromichi AOKI, Hajime SAKANO and
 Yasunobu TAKAGAWA
 RESIN COMPOSITION FOR ELECTROSTATIC COATING
 Our Ref: Q62080

Dear Sir:

The following documents and fees are submitted herewith in connection with the above application for the purpose of entering the National stage under 35 U.S.C. § 371 and in accordance with Chapter II of the Patent Cooperation Treaty:

- ☒ an executed Declaration and Power of Attorney.
- ☒ an English translation of the International Application and executed Translator's Declaration.
- ☒ International Preliminary Examination Report.
- ☒ International Search Report and PTO 1595 form.
- ☒ a Form PTO-1449 listing the ISR references, and a complete copy of each reference.

It is assumed that copies of the International Application, the International Search Report, and any Articles 19 and 34 amendments as required by § 371(c) will be supplied directly by the International Bureau, but if further copies are needed, the undersigned can easily provide them upon request.

The Government filing fee is calculated as follows:

Total claims	12	-	20	=		x	\$18.00	=	\$ 00
Independent claims	1	-	3	=		x	\$80.00	=	\$ 00
Base Fee									\$860.00
Multiple Dependent Claim Fee									\$270.00

TOTAL FILING FEE

\$1130.00

Recordation of Assignment

\$ 40.00

TOTAL FEE

\$1170.00

Checks for the statutory filing fee of \$1130.00 and Assignment recordation fee of \$40.00 are attached. You are also directed and authorized to charge or credit any difference or overpayment to Deposit Account No. 19-4880. The Commissioner is hereby authorized to charge any fees under 37 C.F.R. §§ 1.16, 1.17 and 1.492 which may be required during the entire pendency of the application to Deposit Account No. 19-4880. A duplicate copy of this transmittal letter is attached.

Respectfully submitted,

Waddell A. Biggart
 Registration No. 24,861

WAB/amt

-1-

DESCRIPTION

RESIN COMPOSITION FOR ELECTROSTATIC COATINGTECHNICAL FIELD

The present invention relates to a resin
5 composition for electrostatic coating, a resin article
formed from the resin composition and a formed resin
article produced by coating the resin article
electrostatically.

BACKGROUND ART

10 Rubber-reinforced styrene resin is excellent in
impact resistance, moldability and the like, and utilized
in various fields including vehicle parts, electrical
appliances, business equipment and so on.

Among these fields, the rubber-reinforced
15 styrene resin is chiefly applied to the vehicle parts as
being coated for improving design and weatherability.

However, in the case of coating an article
formed from the rubber-reinforced styrene resin, there
arise problems such as insufficiency in deposition
20 efficiency of a coating composition and difficulty in
maintaining uniformity of the quality of coating surface
when the article has a complicated shape.

Electrostatic coating has heretofore been
performed as a coating method for solving the above
25 problems. However, the electrostatic coating necessitates

a step of subjecting an article surface to a conductive primer treatment since the rubber-reinforced styrene resin inherently is an insulating material. A method of mixing a conductive carbon with the resin has also been employed; however, the method has a drawback that impact strength of a coating film is largely decreased.

DISCLOSURE OF INVENTION

The present invention was accomplished to solve the above problems. A main object of the invention is to provide a resin composition for electrostatic coating which comprises a rubber-reinforced aromatic vinyl resin such as a rubber-reinforced styrene resin and is useful for forming an article excellent in various physical properties such as impact resistance; the article formed from the resin composition being suitably used for forming thereon a satisfactory electrostatic coating film without a conductive primer treatment.

Another object of the invention is to provide a resin article formed from the resin composition comprising a rubber-reinforced aromatic vinyl resin, the resin article being excellent in electrostatic coatability and various physical properties.

The inventors carried out an extensive research considering the conventional techniques mentioned above, and found that it is possible to form a satisfactory

electrostatic coating film, even without a conductive primer treatment, on a resin article formed from a resin composition comprising a specific rubber-reinforced aromatic vinyl resin, a polyamide elastomer, a modified vinyl polymer containing a specific functional group(s), and an alkali metal salt and that the formed article is excellent in various physical properties such as impact resistance, to thereby accomplish the present invention.

Thus, the present invention provides the following resin composition, resin article formed from the resin composition, and formed resin article produced by coating the article electrostatically.

1. A resin composition for electrostatic coating comprising a rubber-reinforced aromatic vinyl resin (A), a polyamide elastomer (B), a modified vinyl polymer (C) containing at least one functional group selected from the group consisting of carboxyl, epoxy, amino and amido, and an alkali metal salt (D).

2. The resin composition according to item 1, wherein the rubber-reinforced aromatic vinyl resin (A) is a graft copolymer obtainable by polymerizing monomer components (a-2) in the presence of a rubber-like polymer (a-1), or a mixture of said graft copolymer and a copolymer of the monomer components (a-2), the monomer components (a-2) comprising (i) an aromatic vinyl monomer,

(ii) at least one monomer selected from the group consisting of a vinyl cyanide monomer and an alkylester monomer of unsaturated carboxylic acid and, when necessary, (iii) another copolymerizable vinyl monomer.

5 3. The resin composition according to item 1, wherein the polyamide elastomer (B) is obtainable by reacting polyol with at least one compound selected from the group consisting of aminocarboxylic acid having not less than 6 carbon atoms, lactam having not less than 6
10 carbon atoms and nylon mn salt ($m + n \geq 12$).

 4. The resin composition according to item 1, wherein the modified vinyl polymer (C) is a copolymer of an ethylenically unsaturated monomer containing at least one functional group selected from the group consisting of
15 carboxyl, epoxy, amino and amido with another ethylenically unsaturated monomer.

 5. The resin composition according to item 1, wherein the alkali metal salt (D) is at least one compound selected from the group consisting of potassium
20 thiocyanate and an alkali metal salt of dodecylbenzenesulfonic acid.

 6. The resin composition according to any one of items 1-5, comprising 2-96.95 wt.% of the rubber-reinforced aromatic vinyl resin (A), 2-96.95 wt.% of the
25 polyamide elastomer (B), 1-50 wt.% of the modified vinyl

polymer (C) and 0.05-10 wt.% of the alkali metal salt (D) when a total amount of the rubber-reinforced aromatic vinyl resin (A), the polyamide elastomer (B), the modified vinyl polymer (C) and the alkali metal salt (D) is 100 wt.%.
5 wt.%.

7. A formed resin article excellent in electrostatic coatability, which is formed from the resin composition according to any one of items 1-6.

8. A formed resin article having electrostatic
10 coating film, which is produced by electrostatically coating the resin article according to item 7.

The resin composition for electrostatic coating of the present invention comprises a rubber-reinforced aromatic vinyl resin (A), a polyamide elastomer (B), a
15 modified vinyl polymer (C) containing at least one functional group selected from the group consisting of carboxyl, epoxy, amino and amido, and an alkali metal salt (D).

Components comprised in the resin composition of
20 the present invention are described below.

(A) Rubber-reinforced aromatic vinyl resin

The rubber-reinforced aromatic vinyl resin is also known as a rubber-reinforced styrene resin, and is obtainable by polymerizing a rubber-like polymer (a-1)
25 with monomer components (a-2) consisting of (i) an

aromatic vinyl monomer, (ii) at least one monomer selected from the group consisting of a vinyl cyanide monomer and an alkylester monomer of unsaturated carboxylic acid and, when necessary, (iii) another copolymerizable vinyl
5 monomer. The rubber-reinforced aromatic vinyl resin may preferably be a graft copolymer obtainable by polymerizing the monomer components (a-2) in the presence of the rubber-like polymer (a-1), or a mixture of the graft copolymer and a copolymer obtainable by polymerizing the
10 monomer components (a-2).

Components constituting the rubber-reinforced aromatic vinyl resin are described below.

(a-1) Rubber-like polymer

Examples of the rubber-like polymer (a-1)

15 includes polybutadiene, a styrene-butadiene copolymer, a acrylonitrile-butadiene copolymer and like diene polymers, an ethylene-propylene copolymer, an ethylene-propylene-unconjugated diene copolymer and like ethylene-propylene copolymers, acrylic ester copolymers, chlorinated
20 polyethylene and the like. These rubber-like polymers (a-1) are used solely or in combination of two or more.

Preparation process of the rubber-like polymer is not limited, and the rubber-like polymer may be prepared by emulsion polymerization, solution
25 polymerization, suspension polymerization, bulk

polymerization or the like according to known conditions.
A gel content of the rubber-like polymer is not limited,
but may preferably be 0-95 %. It is particularly
preferred to prepare the rubber-like polymer by the
5 emulsion polymerization from the viewpoint of
controllability of the gel content.

(a-2) Monomer components

The monomer components (a-2) comprise (i) an
aromatic vinyl monomer, (ii) at least one monomer selected
10 from the group consisting of a vinyl cyanide monomer and
an alkylester monomer of unsaturated carboxylic acid and,
when necessary, (iii) another copolymerizable vinyl
monomer.

Examples of the aromatic vinyl monomer (i)
15 includes styrene, α -methylstyrene, o-methylstyrene, m-
methylstyrene, p-methylstyrene, t-butylstyrene, α -
methylvinyltoluene, dimethylstyrene, chlorostyrene,
dichlorostyrene, bromostyrene, dibromostyrene,
vinyl-naphthalene and the like; among which styrene is
20 particularly preferred. The aromatic vinyl monomer may be
used solely or in combination of two or more.

The vinyl cyanide monomer and the alkylester
monomer of unsaturated carboxylic acid (monomer (ii)) are
used solely or in combination.

25 Examples of the vinyl cyanide monomer include

acrylonitrile, methacrylonitrile, fumaronitrile and the like; among which acrylonitrile is particularly preferred.

Examples of the alkylester monomer of unsaturated carboxylic acid include methyl (meth)acrylate, ethyl (meth)acrylate, propyl (meth)acrylate, 2-ethylhexyl (meth)acrylate and the like; among which methyl methacrylate is particularly preferred.

These monomers may be used solely or in combination of two or more.

10 In the present invention, it is particularly preferred to use the cyanide vinyl monomer as the monomer (ii).

As another copolymerizable vinyl monomer (iii), a monomer copolymerizable with (i) the aromatic vinyl monomer and (ii) at least one monomer selected from the group consisting of the vinyl cyanide monomer and the alkylester monomer of unsaturated carboxylic acid may suitably be used, and, preferably, said another copolymerizable vinyl monomer (iii) is also
15 copolymerizable with the rubber-like polymer.

Specific examples of said another copolymerizable vinyl monomer include acrylic acid, methacrylic acid, maleic acid and like unsaturated carboxylic acids; maleic anhydride, citraconic anhydride
25 and like anhydrides of unsaturated dicarboxylic acid;

maleimide, methylmaleimide, ethylmaleimide, N-phenylmaleimide, O-chloro-N-phenylmaleimide and like maleimide compounds and the like. Said another copolymerizable vinyl monomer may be used solely or in
5 combination of two or more.

(iv) Composition ratio of monomer components (a-2)

Proportions of the aromatic vinyl monomer (monomer (i)), at least one monomer (monomer (ii))
10 selected from the group consisting of a vinyl cyanide monomer and an alkylester monomer of unsaturated carboxylic acid, and another copolymerizable vinyl monomer (monomer (iii)) to be comprised in the monomer components (a-2) are not limited, but the monomer components (a-2)
15 may preferably comprise, when a total amount of monomers (i), (ii) and (iii) is 100 wt.%, 50-90 wt.% of the monomer (i), 50-10 wt.% of the monomer (ii) and 0-40 wt.% of the monomer (iii), more preferably 50-80 wt.% of the monomer (i), 50-20 wt.% of the monomer (ii) and 0-30 wt.% of the
20 monomer (iii).

Preparation of rubber-reinforced aromatic vinyl resin (A)

Preparation process of the rubber-reinforced aromatic vinyl resin (A) is not limited, but preferable is a process wherein a graft copolymer is prepared by
25 polymerizing the monomer components (a-2) in the presence

of the rubber-like polymer (a-1). A known method such as emulsion polymerization, suspension polymerization, bulk polymerization and solution polymerization or a method combining them may be employed for the polymerization.

5 A graft ratio and a weight average particle diameter of the graft copolymer obtained by the above method are not limited, but the graft ratio may preferably be about 20-100 % and the weight average particle diameter may preferably be about 0.05-5 μm .

10 The rubber-reinforced aromatic vinyl resin (A) used in the invention may be the graft copolymer or a mixture of the graft copolymer and the copolymer of the monomer components (a-2).

 The rubber-reinforced aromatic vinyl resin (A)
15 may preferably comprise 100-10 wt.% of the graft copolymer and 0-90 wt.% of the copolymer of the monomer components (a-2) when a total amount of the graft copolymer and the copolymer of the monomer components (a-2) is 100 wt.%. If the proportion of the graft copolymer is less than 10 wt.%,
20 the resulting composition will undesirably be deteriorated in impact resistance.

 In the preparation process of the graft copolymer, a copolymer of the monomer components (a-2) is produced as a by-product. The proportion of the graft
25 copolymer mentioned above includes the amount of the by-

product copolymer of the monomer components (a-2). In the present specification, "proportion of the copolymer of the monomer components (a-2)" means the proportion of the copolymer of the monomer components (a-2) prepared

5 separately from the graft copolymer. A method for polymerizing the monomer components (a-2) is not limited, and a known method such as emulsion polymerization, suspension polymerization, bulk polymerization and solution polymerization or a method combining them may be
10 employed for the polymerization.

Proportions of the rubber-like polymer (a-1) and the monomer components (a-2) to be used for the preparation of the rubber-reinforced aromatic vinyl resin (A) are not limited, but it is preferable to use, when a
15 total amount of the rubber-like polymer (a-1) and the monomer components (a-2) is 100 wt.%, 5-80 wt.% of the rubber-like polymer (a-1) and 95-20 wt.% of the monomer components (a-2), in particular, 5-60 wt.% of the rubber-like polymer (a-1) and 95-40 wt.% of the monomer
20 components (a-2). Here, in the case of employing only a graft polymer, the above proportions are those of the rubber-like polymer (a-1) and the monomer components (a-2) in the graft polymer and, in the case of employing a mixture of the graft polymer and the copolymer, the above
25 proportions are those of the rubber-like polymer (a-1) and

the monomer components (a-2) in the mixture.

(B) Polyamide elastomer

The polyamide elastomer (B) is also known as a polyetherester amide, and is obtainable by reacting at
5 least one component selected from the group consisting of aminocarboxylic acid having not less than 6 carbon atoms, lactam having not less than 6 carbon atoms and nylon mn salts ($m + n \geq 12$) as a hard segment (hereinafter sometimes referred to as "component (X)") with polyol as a
10 soft segment (hereinafter sometimes referred to as "component (Y)").

Among the component (X), upper limit of the number of carbon atoms of the aminocarboxylic acid having not less than 6 carbon atoms may preferably be about 12;
15 examples of such aminocarboxylic acid include ω -aminopropionic acid, ω -aminoenanthic acid, ω -aminocaprolic acid, ω -aminopelargonic acid, ω -aminocapric acid, 11-aminoundecanoic acid, 12-aminododecanoic acid and the like.

Upper limit of the number of carbon atoms of the
20 lactam having not less than 6 carbon atoms may preferably be about 12; specific examples of such lactam include caprolactam, laurolactam and the like.

The nylon mn salts ($m + n \geq 12$) are the salts comprising equimolar amounts of dicarboxylic acid having
25 not less than 6 carbon atoms, preferably 6-12 carbon atoms,

and diamine having not less than 6 carbon atoms, preferably 6-12 carbon atoms; specific examples of such nylon mn salts include nylon 6·6 salt, nylon 6·10 salt, nylon 6·12 salt, nylon 11·6 salt, nylon 11·10 salt, nylon 11·12 salt, nylon 12·6 salt, nylon 12·10 salt, nylon 12·12 salt and the like.

Poly(alkyleneoxide)glycol may be used as the polyol which is the component (Y). Specific examples of the polyol include, polyethyleneglycol, poly(1,2 and 1,3 propyleneoxide)glycol, poly(tetramethyleneoxide)glycol, poly(hexamethyleneoxide)glycol, a block or random copolymer of ethyleneoxide and propyleneoxide, a block or random copolymer of ethyleneoxide and tetrahydrofuran, and the like. Average molecular weight of each of the polyol may suitably be about 500-3000.

Preparation process of the polyamide elastomer (B) is not limited, and a known process may be employed in the present invention. The polyamide elastomer (B) is obtainable by, for example, a process wherein a polyamide prepolymer is formed by reacting component (X) with dicarboxylic acid to prepare polyamide prepolymer, and then the polyamide prepolymer is polymerized with polyol, which is the component (Y), under a high temperature and a reduced pressure, a process wherein a carboxylic acid-terminated polyamide elastomer is produced by charging a

reaction vessel with the component (X), component (Y) and dicarboxylic acid simultaneously, followed by reacting them at a high temperature and under an increased pressure and then the polyamide elastomer is polymerized under a
5 normal pressure or a reduced pressure, or the like.

Dicarboxylic acid used in the preparation of the polyamide elastomer (B) may preferably have 4-20 carbon atoms; examples of which include terephthalic acid, isophthalic acid, phthalic acid, naphthalene-2,6-
10 dicarboxylic acid, naphthalene-2,7-dicarboxylic acid, diphenyl-4,4-dicarboxylic acid, diphenoxyethanedicarboxylic acid, sodium 3-sulfoisophthalate and like aromatic dicarboxylic acids, 1,4-cyclohexanedicarboxylic acid, 1,2-
15 cyclohexanedicarboxylic acid, dicyclohexyl-4,4-dicarboxylic acid and like alicyclic dicarboxylic acids, succinic acid, oxalic acid, adipic acid, dicarboxylic acid and the like.

Ratio of the component (X) and the component (Y)
20 may be such that proportion of the component (X) based on a total amount of the component (X) and the component (Y) is about 95-10 wt.%, preferably about 90-20 wt.%. If the proportion of the component (X) is higher than 95 wt.%, the resulting resin composition will be deteriorated in
25 flexibility. In turn, if the proportion is lower than 10

wt.%, the resulting resin composition is tend to be deteriorated in chemical resistance.

The polyamide elastomer to be used in the present invention may suitably have a weight average
5 molecular weight of about 5,000-100,000.

Specific examples of the usable polyamide elastomer include those disclosed in Japanese Unexamined Patent Publications Nos. 232450/1987, 33456/1988, 95251/1988, 60647/1989, 240553/1989, 97751/1991,
10 309547/1992, 314741/1992, 348150/1992, 230365/1993, 262971/1993, 287161/1993, 295191/1993, 320497/1993, 313079/1994, 10989/1995, 145368/1995, 188475/1995, 188476/1995 and the like.

(C) Modified vinyl polymer

15 The modified vinyl polymer (C) to be used in the present invention comprises as a base skeleton a vinyl polymer obtainable by polymerizing at least one vinyl monomer, and contains in the vinyl polymer at least one functional group selected from the group consisting of
20 carboxyl, epoxy, amino and amido. At least one of these functional groups must be present per molecule.

Specific examples of such modified vinyl polymer include (1) a polymer obtainable by polymerizing an ethylenically unsaturated monomer having a functional
25 group(s), (2) a copolymer of an ethylenically unsaturated

monomer having a functional group(s) and another ethylenically unsaturated monomer, (3) a polymer obtainable by polymerizing an ethylenically unsaturated monomer using an initiator having a functional group(s) and/or a chain transfer agent having a functional group(s) to introduce a functional group(s) to a molecular chain of the polymer.

Among the modified vinyl polymers to be used in the invention, specific examples of the ethylenically unsaturated monomer having a functional group(s) usable for the production of the polymer (1) or (2) are as follows.

Examples of the ethylenically unsaturated monomer having carboxyl include acrylic acid, methacrylic acid, maleic acid, maleic anhydride, itaconic acid and the like. Examples of the ethylenically unsaturated monomer having epoxy include glycidyl acrylate, glycidyl methacrylate, glycidyl itaconate and the like. Examples of the ethylenically unsaturated monomer having amino include aminoethyl acrylate, ethylaminopropyl methacrylate, phenylaminoethyl methacrylate and like aminoalkylester derivatives of (meth)acrylic acid, N-acetylvinylamine and like vinylamine derivatives, methallylamine and like allylamine derivatives, aminostyrene and the like.

Examples of the ethylenically unsaturated monomer having

amido include acrylamide, N-methylmethacrylamide and the like.

Examples of said another ethylenically unsaturated monomer usable for the production of the

5 polymer (2) include styrene, α -methylstyrene, vinyltoluene and like aromatic vinyl monomers, acrylonitrile, methacrylonitrile and like vinyl cyanide monomers, methyl acrylate, methyl methacrylate, ethyl acrylate, ethyl methacrylate and like ester monomers of

10 ethylenically unsaturated carboxylic acid, maleimide, N-phenylmaleimide, N-cyclohexylmaleimide and like maleimide monomers and the like.

Examples of the initiator having a functional group(s) usable for the production of the polymer (3)

15 include those having carboxyl such as γ , γ' -azobis(γ -cyanovaleric acid) and succinic acid peroxide, those having amino such as α , α' -azobis(γ -amino- α , γ -divaleronitrile), p-aminobenzoylperoxide, and the like. Examples of the chain transfer agent having a functional group(s) include

20 those having carboxyl such as mercaptopropionic acid, 4-mercaptopbenzoic acid and thioglycolic acid and those having amino such as mercaptomethylamine, N-(β -mercaptoethyl)-N-methylamine, bis-(4-aminophenyl)disulfide, mercaptoaniline, and like chain transfer agents.

25 Polymerization method for preparing the modified

vinyl polymer (C) is not limited, and may be any one of suspension polymerization, bulk polymerization, emulsion polymerization, solution polymerization and the like.

Known initiators and chain transfer agents may be used for the production of the polymer (1) or (2). Examples of the initiators include a peroxide such as potassium persulfate, hydrogen peroxide, benzoyl peroxide and lauroyl peroxide, an azo compound such as azobisisobutyronitrile, and oxidation-reduction initiators comprising an iron salt and an organic hydroperoxide such as cumenehydroperoxide. Examples of the chain transfer agent include n-dodecylmercaptan, t-dodecylmercaptan and like mercaptanes, α -methylstyrene dimer, terpinolene and the like.

In the production of the polymer (2), proportions of the ethylenically unsaturated monomer having a functional group(s) and said another ethylenically unsaturated monomer may differ depending on types of monomers to be used; however, there may preferably be used, based on a total amount thereof, about 0.01-99 wt.% of the ethylenically unsaturated monomer having a functional group(s) and about 1-99.99 wt.% of said another ethylenically unsaturated monomer, more preferably about 0.05-80 wt.% of the ethylenically unsaturated monomer having a functional group(s) and about

20-99.95 wt.% of said another ethylenically unsaturated monomer, particularly preferably about 0.15-50 wt.% of the ethylenically unsaturated monomer having a functional group(s) and about 50-99.9 wt.% of said another
5 ethylenically unsaturated monomer.

Further, in the production of the polymer (3), amounts of the initiator having a functional group(s) and the chain transfer agent having a functional group(s) used for the polymerization of the ethylenically unsaturated
10 monomer are not limited, but there may typically be used, based on 100 parts by weight of the ethylenically unsaturated monomer, about 0.01-5 parts by weight of the initiator and about 0.01-10 parts by weight of the chain transfer agent. The initiator and the chain transfer
15 agent each having a functional group(s) may be used together, while they may be used in such a manner that one of them has a functional group(s) and the other does not. The ethylenically unsaturated monomer to be used in the production process of the polymer (3) does not necessarily
20 have a functional group; however, it is of course possible to use an ethylenically unsaturated monomer having a functional group(s).

It is preferred to use the polymer (2) in the present invention from the viewpoints of easiness of
25 adjusting a content of the functional group comprised in

the polymer and balance of physical properties of the resulting composition.

(D) Alkali metal salt

Examples of the alkali metal salt (D) include

- 5 lithium chloride, lithium bromide, lithium iodide, sodium
iodide, sodium borohydride, lithium borofluoride,
potassium borofluoride, lithium tetraphenylborate,
potassium tetraphenylborate, sodium tetraphenylborate,
lithium thiocyanate, sodium thiocyanate, potassium
10 thiocyanate, lithium perchlorate, sodium perchlorate,
potassium perchlorate and like alkali metal salts of
inorganic acid; lithium trifluoroacetate, sodium
trifluoroacetate, potassium trifluoroacetate, lithium
trifluoromethanesulfonate, sodium
15 trifluoromethanesulfonate, potassium
trifluoromethanesulfonate, lithium acetate, sodium acetate,
potassium acetate, lithium dodecylbenzenesulfonate,
potassium dodecylbenzenesulfonate, sodium
dodecylbenzenesulfonate, lithium dodecylsulfonate,
20 potassium dodecylsulfonate, sodium dodecylsulfonate and
like alkali metal salts of organic acid and the like.
These metal salts may be used solely or in combination of
two or more.

- Among these alkali metal salts, potassium
25 thiocyanate and an alkali metal salt of a nuclear

substitution product of benzenesulfonic acid such as dodecylbenzenesulfonic acid may preferably be used in the present invention.

Resin composition of the present invention and resin

5 article formed therefrom

The resin composition of the invention comprises the rubber-reinforced aromatic vinyl resin (A), the polyamide elastomer (B), the modified vinyl polymer (C) having at least one functional group selected from the
10 group consisting of carboxyl, epoxy, amino and amido and the alkali metal salt (D).

Form of the resin composition of the invention is not limited insofar as the resin composition comprises the above four components. For example, each of the
15 components may be mixed in the form of a powder or the like, but they may typically be mixed and melted to give a resin composition in the form of pellets so as to be used for the production of resin articles.

Method of mixing the components and order of the
20 components to be added are not limited, and the components may be mixed simultaneously or by a multistage mixing comprising plural steps such as a step of mixing two or three components and a step of mixing the rest of the components. A known mixing apparatus such as a kneader,
25 Banbury mixer, roll or the like may be used for mixing the

components. After the mixing process, the mixture is pelletized by an ordinary pelletizer or the like to give a composition in the form of pellets.

Proportions of the components to be comprised in
5 the resin composition of the present invention is not crucial, but the resin composition may preferably comprise about 2-96.95 wt.% of the rubber-reinforced aromatic vinyl resin (A), about 2-96.95 wt.% of the polyamide elastomer (B), about 1-50 wt.% of the modified vinyl polymer (C) and
10 about 0.05-10 wt.% of the alkali metal salt (D) when a total amount of the four components (A)-(D) is 100 wt.%. The resin composition obtained by mixing the components (A)-(D) in the above ratio is good in fluidity and so on and excellent in moldability. Further, it is possible to
15 form a satisfactory electrostatic coating on a article formed from the resin composition without applying a conductive primer. Moreover, the article is excellent in various physical properties such as impact resistance, mechanical strength and the like and good in dimensional
20 stability, appearance and so on.

In the case where the proportion of the rubber-reinforced aromatic vinyl resin (A) is too low, the resulting composition will be deteriorated in fluidity, and an article formed therefrom will be insufficient in
25 impact resistance and mechanical strength and further be

deteriorated in appearance and dimensional stability. In turn, if the proportion is too high, deposition efficiency of coating composition cannot be improved.

In the case where the proportion of the
5 polyamide elastomer (B) is too low, deposition efficiency of coating composition cannot be improved. In turn, if the proportion is too high, the article formed from the resulting composition will be deteriorated in rigidity.

In the case where the proportion of the modified
10 vinyl polymer (C) is too low, the article formed from the resulting composition will be deteriorated in water resistance and adhesion of coating. In turn, if the proportion is too high, the resulting composition will be deteriorated in fluidity, and an article formed therefrom
15 will be deteriorated in mechanical resistance and appearance.

In the case where the proportion of the alkali metal salt (D) is too low, deposition efficiency of coating composition cannot be improved. In turn, if the
20 proportion is too high, an article formed from the resulting composition will be deteriorated in thermostability and appearance.

More preferably, the resin composition of the present invention may comprise about 50-90 wt.% of the
25 rubber-reinforced aromatic vinyl resin (A), about 5-50

wt.% of the polyamide elastomer (B), about 3-20 wt.% of the modified vinyl polymer (C) and about 0.2-5 wt.% of the alkali metal salt (D), based on 100 wt.% of a total amount of the four components (A)-(D), from the viewpoints of
5 being good not only in deposition efficiency of coating composition but also in mechanical properties such as rigidity.

To the resin composition of the present invention, it is possible to add, when so required, an
10 antioxidant (for example, 2,6-di-t-butyl-4-methylphenol, 2-(1-methylcyclohexyl)-4,6-dimethylphenol, 2,2-methylenebis-(4-ethyl-6-t-methylphenol), 4-4'-thiobis-(6-t-butyl-3-methylphenol), dilaurylthiodipropionate, tris(di-nonylphenyl)phosphite, wax), an ultraviolet absorbent (for
15 example, p-t-butylphenyl salicylate, 2,2'-dihydroxy-4-methoxybenzophenone, 2-(2'-hydroxy-4'-n-octoxyphenyl)benzotriazole), a lubricant (for example, paraffine wax, stearic acid, hardened oil, stearamide, methylenebisstearamide, ethylenbisstearamide, n-butyl
20 stearate, ketone wax, octyl alcohol, lauryl alcohol, hydroxystearic acid triglyceride), a flame retarder (for example, antimonous oxide, aluminium hydroxide, zinc borate, tricresyl phosphate, tris(dichloropropyl)phosphate, chlorinated paraffine, tetrabromobutane, hexabromobenzene,
25 tetrabromobisphenol A), a colorant (for example, titanium

oxide, carbon black), a filler (for example, calcium carbonate, clay, silica, glass fiber, glass beads, carbon fiber), a pigment and the like.

Amounts of these additives are not limited, and
5 may suitably be adjusted depending on the purposes of using them. A total amount of the additives to be used may typically be about 0.01-100 parts by weight, preferably about 0.01-50 parts by weight, based on 100 parts by weight of a total amount of the components (A)-
10 (D).

Further, when so required, another thermoplastic resin such as polycarbonate, polyvinyl chloride, polyamide, polybutylene terephthalate, polyethylene terephthalate, polyphenylene oxide and polyoxymethylene may be mixed with
15 the resin composition of the present invention.

Amounts of the thermoplastic resins are not limited, and they may suitably be adjusted depending on the purposes of using them. A total amount of the thermoplastic resins to be used may typically be about 1-
20 100 parts by weight, preferably 1-50 parts by weight, based on 100 parts by weight of a total amount of the components (A)-(D).

When forming the resin composition of the present invention into a desired shape, a forming method
25 may be selected from conventional methods depending on the

type of the target article. For example, the resin composition in the form of pellets as mentioned above may suitably be formed by a known forming method such as injection molding, extrusion forming, compression molding, 5 blow molding and the like at a melted resin temperature of about 200-280°C and at a mold temperature of about 30-100°C.

The article formed from the resin composition of the present invention is good in electrostatic coatability 10 and, therefore, it is possible to form an electrostatic coating on the article by an ordinary method without conductive primer treatment. The coating thus formed is uniform in its coating surface quality even when the article had a complicated shape and is good in adhesion.

15 EFFECT OF THE INVENTION

The resin composition of the present invention is good in fluidity and moldability, and it is possible to form a satisfactory electrostatic coating on the article formed from the resin composition without a conductive 20 primer. The article is excellent in various physical properties such as impact resistance and mechanical strength, and good in dimensional stability, appearances and the like.

The resin article has various applications such 25 as vehicle parts, electric appliances, business equipment,

etc. and, in particular, is suitably used for the vehicle parts.

BEST MODE FOR CARRYING OUT THE INVENTION

The present invention will be illustrated in the following based on examples, but the invention is not limited to the examples. In addition, "parts" and "%" in the composition ratios are based on weights unless otherwise stated.

(Examples 1-3 and Comparative Examples 1-5)

Components used in the examples and comparative examples are as follows.

Rubber-reinforced aromatic vinyl resin (A)

A-1: 20 parts (solid content) of polybutadiene latex (average particle diameter: 0.35 μ m; gel content: 80 %), 55 parts of styrene and 25 parts of acrylonitrile are polymerized by a known emulsion polymerization method. Obtained polymer latex was subjected to a salting-out treatment, dehydration and drying to give A-1.

Polyamide elastomer (B)

B-1: polyetherester amide ("PELESTAT IOS-6321", a product of Sanyo Chemical Industries, Ltd.).

B-2: polyetherester amide ("PEBAX 4011MA", a product of Toray Industries, Inc.).

Modified vinyl polymer (C)

C-1: 70 parts of styrene, 27 parts of acrylonitrile and 3

parts of acrylic acid are polymerized by a known emulsion polymerization method. Obtained polymer latex was subjected to a salting-out treatment, dehydration and drying to give C-1.

5 Alkali metal salt (D)

D-1: sodium dodecylbenzenesulfonate.

Above components were mixed in the proportions shown in Table 1. Compositions thus obtained were melted and kneaded by a uniaxial extruder at a temperature of 220°C to give pellets. As to the pellets, physical properties were measured according to the following methods. The measurement methods are described below. Results of the measurements are shown in Table 1.

15 Impact resistance (notched Izot)

By a method according to ASTM D-256, a test piece having a thickness of 1/4 inch was prepared from each of the compositions at a temperature of 230°C, and a notched Izot impact value of the test piece was measured at a temperature of 23°C.

Fluidity

By a method according to ASTM D-1238, the fluidity was measured under the conditions of a melting temperature of 240°C and with a load of 10 kg.

25 Rigidity

By a method according to ASTM D-790, a test piece having a thickness of 1/4 inch was prepared from each of the compositions at a temperature of 230°C and a flexural modulus of the test piece was measured at a temperature of 23°C.

Molding shrinkage

An article was molded from each of the compositions by injection molding at a temperature of 230°C using a mold having an impression of 150 mm x 90 mm x 3 mm. After allowing the article to stand for 72 hours at a room temperature, size thereof was measured with the accuracy of second decimal places (in millimeters) by using calipers, and the molding shrinkage was calculated from the following expression:

Molding shrinkage (%) =
(mold dimension - size of article) x 100/mold dimension.

Surface resistivity

An article was molded from each of the compositions by injection molding at a temperature of 230°C using a mold having an impression of 150 mm x 90 mm x 3 mm. After conditioning the test piece under the conditions of a temperature of 23°C and a relative humidity of 55 % for 24 hours, the surface resistivity of the test piece was measured by using a surface resistivity meter "SM-10E" (product of Toa Electronics Ltd.), under

the conditions of a measuring voltage of 500 V and a sampling time of 10 seconds.

Appearance of article

An article was molded from each of the
5 compositions by injection molding at a temperature of
230°C using a mold having an impression of 95 mm x 55 mm x
3 mm. The article was visually observed of its evenness
of luster for evaluation of its appearance, and the
evaluation is shown based on the following criteria:

10 A: good; to C: bad.

Weight and adhesion of coating

An article was molded from each of the
compositions by injection molding at a temperature of
230°C using a mold having an impression of 240 mm x 250 mm
15 x 3.5 mm. Electrostatic coating was applied on the
article under the following conditions.

Coating device:

Reciprocating rotary electrostatic coating
device (IVW bell-shaped coating device, product
20 of Honda Engineering Co., Ltd.);
Bell diameter: 70 ϕ ;
Applied voltage: -60 Kv;
Discharge rate: 100 g/min;
Distance between gun and molded article: 200 mm;
25 Revolution: 10000 rpm;

Shaving air: 0.4 kg;

CV speed: 5400 mm/min;

Reciprocating speed: 2600 mm/min.

Coating material:

- 5 Two-pack type curable urethane coating
composition (HIGH URETHANE #5000 and # 6500,
products of NOF Corporation).

Coating conditions:

Temperature of 27°C; humidity of 65 %RH.

10

After performing the electrostatic coating under
the above conditions, the coated article was allowed to
stand for 2 hours at a temperature of 80°C to be dried.
Then, a weight of coating formed on the article was
15 measured.

Further, adhesion of the coating formed on the
article was measured by the following method.

- First, the coating film was cross-cut to reach
the body of the article in order to form 100 cells (10 x
20 10) of 1 mm square using a middling razor, the cutting
edge thereof being retained at an angle of about 30 degree
with respect to the coating film. Then, a cellophane
adhesive tape having a width of 24 mm was brought into
close contact with the cross-cut portion, and the tape was
25 instantly peeled off while one end thereof was retained at

right angle with respect to the surface of the article, to thereby examine the adhesion of coating. Results are expressed by number of cells peeled off/number of tested cells (100).

- 5 Adhesion of the coating was measured under the following conditions.

 Condition 1: Adhesion was measured after allowing a coated article to stand for 120 hours at a humidity of 95 % and a temperature of 50°C.

- 10 Condition 2: Adhesion was measured after allowing a coated article to stand for 240 hours at a humidity of 95 % and a temperature of 50°C.

	Example			Comparative Example				
	1	2	3	1	2	3	4	5
-Proportions- (parts)								
A-1	70	50	85	100	80	40	70	25
B-1	18	18	8	-	20	58	20	18
B-2	-	15	-	-	-	-	-	-
C-1	10	15	5	-	-	-	10	55
D-1	2	2	2	-	-	2	-	2
-Physical Properties-								
Impact Resistance (kg·cm/cm)	28	32	22	20	23	42	27	12
Fluidity (g/10 min)	36	61	28	25	43	68	35	17
Rigidity (kg/cm ²)	1.8x10 ⁴	1.4x10 ⁴	1.8x10 ⁴	2.4x10 ⁴	1.7x10 ⁴	0.9x10 ⁴	1.8x10 ⁴	2.1x10 ⁴
Molding Shrinkage(%)	0.6	0.9	0.6	0.5	0.6	1.1	0.7	0.6
Surface Resistivity (Ω)	2.0x10 ⁹	7.0x10 ⁸	1.0x10 ¹⁰	>10 ¹⁶	3.0x10 ¹²	7.0x10 ⁷	3.5x10 ¹¹	5.2x10 ⁹
Appearance	A	A	A	A	A	A	A	C
Weight of Coating (g)	1.02	1.09	0.85	0.17	0.55	1.12	0.52	0.82
Adhesion: Condition 1	100/100	100/100	100/100	100/100	3/100	0/100	100/100	100/100
Condition 2	100/100	100/100	100/100	100/100	0/100	0/100	100/100	100/100

CLAIMS

1. A resin composition for electrostatic coating comprising a rubber-reinforced aromatic vinyl resin (A), a polyamide elastomer (B), a modified vinyl polymer (C)
5 containing at least one functional group selected from the group consisting of carboxyl, epoxy, amino and amido, and an alkali metal salt (D).

2. The resin composition according to claim 1, wherein the rubber-reinforced aromatic vinyl resin (A) is
10 a graft copolymer obtainable by polymerizing monomer components (a-2) in the presence of a rubber-like polymer (a-1), or a mixture of said graft copolymer and a copolymer of the monomer components (a-2), the monomer components (a-2) comprising (i) an aromatic vinyl monomer,
15 (ii) at least one monomer selected from the group consisting of a vinyl cyanide monomer and an alkylester monomer of unsaturated carboxylic acid and, when necessary, (iii) another copolymerizable vinyl monomer.

3. The resin composition according to claim 1,
20 wherein the polyamide elastomer (B) is obtainable by reacting polyol with at least one compound selected from the group consisting of aminocarboxylic acid having not less than 6 carbon atoms, lactam having not less than 6 carbon atoms and nylon mn salt ($m + n \geq 12$).

25 4. The resin composition according to claim 1,

wherein the modified vinyl polymer (C) is a copolymer of an ethylenically unsaturated monomer containing at least one functional group selected from the group consisting of carboxyl, epoxy, amino and amido with another

5 ethylenically unsaturated monomer.

5. The resin composition according to claim 1, wherein the alkali metal salt (D) is at least one compound selected from the group consisting of potassium thiocyanate and an alkali metal salt of

10 dodecylbenzenesulfonic acid.

6. The resin composition according to any one of claims 1-5, comprising 2-96.95 wt.% of the rubber-reinforced aromatic vinyl resin (A), 2-96.95 wt.% of the polyamide elastomer (B), 1-50 wt.% of the modified vinyl
15 polymer (C) and 0.05-10 wt.% of the alkali metal salt (D) when a total amount of the rubber-reinforced aromatic vinyl resin (A), the polyamide elastomer (B), the modified vinyl polymer (C) and the alkali metal salt (D) is 100 wt.%.

20 7. A formed resin article excellent in electrostatic coatability, which is formed from the resin composition according to any one of claims 1-6.

8. A formed resin article having electrostatic coating film, which is produced by electrostatically
25 coating the resin article according to claim 7.

ABSTRACT

A resin composition for electrostatic coating, comprising a rubber-reinforced aromatic vinyl resin (A), a polyamide elastomer (B), a modified vinyl polymer (C)
5 containing at least one functional group selected from among carboxyl, epoxy, amino and amido, and an alkali metal salt (D); a formed resin article excellent in electrostatic coatability which is formed from the resin composition; and a formed resin article having
10 electrostatic coating film which is produced by coating the articles electrostatically.

Declaration and Power of Attorney for Patent Application

特許出願宣言書及び委任状

Japanese Language Declaration

日本語宣言書

下記の氏名の発明者として、私は以下の通り宣言します。

私の住所、私書箱、国籍は下記の私の氏名の後に記載された通りです。

下記の名称の発明に関して請求範囲に記載され、特許出願している発明内容について、私が最初かつ唯一の発明者(下記の氏名が一つの場合)もしくは最初かつ共同発明者であると(下記の名称が複数の場合)信じています。

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated next to my name,

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled

RESIN COMPOSITION FOR ELECTROSTATIC COATING

上記発明の明細書(下記の欄でX印がついていない場合は、本書に添付)は、

the specification of which is attached hereto unless the following box is checked:

☐ 月 日に提出され、米国出願番号または特許協定条約

国際出願番号を _____ とし、

(該当する場合) _____ に訂正されました。

☒ was filed on June 12, 1998
as United States Application Number or
PCT International Application Number

PCT/JP98/02610 and was amended on

_____ (if applicable).

私は、特許請求範囲を含む上記訂正後の明細書を検討し、内容を理解していることをここに表明します。

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above.

私は、連邦規則法典第37編第1条56項に定義されるとおり、特許資格の有無について重要な情報を開示する義務があることを認めます。

I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, Section 1.56.

Japanese Language Declaration

(日本語宣言書)

私は、米国特許法典第35編第119条(a)-(d)項又は第365条(b)項に基づき下記の、米国以外の国の少なくとも一方国を指定している特許協力条約第365条(a)項に基づく国際出願、又は外国での特許出願もしくは発明者証の出願についての外国優先権をここに主張するとともに、優先権を主張している本出願の前に出願された特許または発明者証の外国出願を以下に、枠内をマークすることで、示しています。

Prior Foreign Applications

外国での先行出願

(Number) (番号)	(Country) (国名)
(Number) (番号)	(Country) (国名)
(Number) (番号)	(Country) (国名)

私は、第35編米国特許法典第119条(e)項に基づいて下記の米国特許出願規定に記載された権利をここに主張致します。

(Application No.) (出願番号)	(Filing Date) (出願日)
-----------------------------	------------------------

私は、下記の米国特許法典第35編第120条に基づいて下記の米国特許出願に記載された権利、又は米国を指定している特許協力条約第365条(c)に基づく権利をここに主張します。又、本出願の各請求範囲の内容が米国特許法典第35編第112条第1項又は特許協力条約で規定された方法で先行する米国特許出願に開示されていない限り、その先行米出願書提出日以降で本出願書の日本国内又は特許協力条約国際出願提出日までの期間中に入手された、連邦規則法典第37編第1条第56項で定義された特許資格の有無に関する重要な情報について開示義務があることを認識しています。

(Application No.) (出願番号)	(Filing Date) (出願日)
(Application No.) (出願番号)	(Filing Date) (出願日)

私は、私自身の知識に基づいて本宣言中で私が行う表明が真実であり、かつ私の入手した情報と私の信ずるところに基づく表明が全て真実であると信じていること、さらに故意になされた虚偽の表明及びそれと同等の行為は米国特許法典第18編第1001条に基づき、罰金または拘禁、もしくはその両方により処罰されること、そしてそのような故意による虚偽の声明を行えば、出願した、又は既に許可された特許の有効性が失われることを認識し、よってここに上記のごとく宣誓を致します。

I hereby claim foreign priority under Title 35, United States Code, Section 119(a)-(d) or 365(b) of any foreign application(s) for patent or inventor's certificate, or 365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or PCT International application having a filing date before that of the application on which priority is claimed.

Priority Not Claimed

優先権主張なし

(Day/Month/Year Filed) (出願年月日)	<input type="checkbox"/>
(Day/Month/Year Filed) (出願年月日)	<input type="checkbox"/>
(Day/Month/Year Filed) (出願年月日)	<input type="checkbox"/>

I hereby claim the benefit under Title 35, United States Code, Section 119(e) of any United States provisional application(s) listed below.

(Application No.) (出願番号)	(Filing Date) (出願日)
-----------------------------	------------------------

I hereby claim the benefit of Title 35, United States Code Section 120 of any United States application(s), or 365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of Title 35, United States Code Section 112, I acknowledge the duty to disclose any material information which is material to patentability as defined in Title 37, Code of Federal Regulations, Section 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of this application:

(Status: Patented, Pending, Abandoned) (現況: 特許許可済、係属中、放棄済)
(Status: Patented, Pending, Abandoned) (現況: 特許許可済、係属中、放棄済)

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Japanese Language Declaration

(日本語宣言書)

委任状: 私は、下記の発明者として、本出願に関する一切の手続きを米国特許商標局に対して遂行する弁理士又は代理人として、下記のものを指名致します。(弁理士、又は代理人の氏名及び登録番号を明記のこと)

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith (list name and registration number)

John H. Mion, Reg. No. 18,879; Thomas J. Macpeak, Reg. No. 19,292; Robert J. Seas, Jr., Reg. No. 21,092; Darryl Mexic, Reg. No. 23,063; Robert V. Sloan, Reg. No. 22,775; Peter D. Olexy, Reg. No. 24,513; J. Frank Osha, Reg. No. 24,625; Waddell A. Biggart, Reg. No. 24,861; Louis Gubinsky, Reg. No. 24,835; Neil B. Siegel, Reg. No. 25,200; David J. Cushing, Reg. No. 28,703; John R. Inge, Reg. No. 26,916; Joseph J. Ruch, Jr., Reg. No. 26,577; Sheldon I. Landsman, Reg. No. 28,430; Richard C. Turner, Reg. No. 29,710; Howard L. Bernstein, Reg. No. 25,665; Alan J. Kasper, Reg. No. 25,426; Kenneth J. Burchfiel, Reg. No. 31,333; Gordon Kit, Reg. No. 30,764; Susan J. Mack, Reg. No. 30,951; Frank L. Bernstein, Reg. No. 31,454; Mark Boland, Reg. No. 32,197; William H. Mandir, Reg. No. 32,156; Scott M. Daniels, Reg. No. 32,562; Brian W. Hannon, Reg. No. 32,778; Abraham J. Rosner, Reg. No. 33,276; Bruce E. Kramer, Reg. No. 33,725; Paul F. Neils, Reg. No. 33,102 and Brett S. Sylvester, Reg. No. 32,765

29

書類送付先:

Send Correspondence to:

SUGHRUE, MION, ZINN, MACPEAK & SEAS, PLLC
2100 Pennsylvania Avenue, N.W., Washington, D.C. 20037-3202

直通電話連絡先: (名称及び電話番号)

Direct Telephone Calls to: (name and telephone number)

(202)293-7060

唯一又は第一発明者名	Full name of sole or first inventor
発明者の署名	Inventor's signature
日付	Date
住所	Residence
国籍	Citizenship
郵便の宛先	Post office address
第二共同発明者名 (該当する場合)	Full name of second joint inventor, if any
第二発明者の署名	Second inventor's signature
日付	Date
住所	Residence
国籍	Citizenship
郵便の宛先	Post office address

(第三以降の共同発明者についても同様に記載し、署名をする (Supply similar information and signature for third and subsequent joint inventors).)

Japanese Language Declaration (日本語宣言書)

第三共同発明者名 (該当する場合)		Full name of third joint inventor, if any	
第三発明者の署名	日付	Third inventor's signature	Date
		<i>Aoki Hiromichi</i>	November 20, 2000
住所		Residence	
		Takatsuki-shi, <u>Osaka</u> 569-1046, Japan <i>SPX</i>	
国籍		Citizenship	
		Japan	
郵便の宛先		Post office address	
		c/o NIPPON A&L INC., 10-1, Tsukahara 2-chome, Takatsuki-shi, Osaka 569-1046, Japan	
第四共同発明者名 (該当する場合)		Full name of fourth joint inventor, if any	
第四発明者の署名	日付	Fourth inventor's signature	Date
		<i>Sakano Hajime</i>	November 20, 2000
住所		Residence	
		199, Sukhumvit Soi 22, <u>Bangkok</u> 10110, Thailand <i>THX</i>	
国籍		Citizenship	
		Japan	
郵便の宛先		Post office address	
		199, Sukhumvit Soi 22, Bangkok 10110, Thailand	
第五共同発明者名 (該当する場合)		Full name of fifth joint inventor, if any	
第五発明者の署名	日付	Fifth inventor's signature	Date
		<i>Takagawa Yasunobu</i>	November 20, 2000
住所		Residence	
		Ibaraki-shi, <u>Osaka</u> 567-0021, Japan <i>SPX</i>	
国籍		Citizenship	
		Japan	
郵便の宛先		Post office address	
		Niwa Manshon 305, 2-24-21, Mishimaoka, Ibaraki-shi, Osaka 567-0021, Japan	
第六共同発明者名 (該当する場合)		Full name of sixth joint inventor, if any	
第六発明者の署名	日付	Sixth inventor's signature	Date
住所		Residence	
国籍		Citizenship	
郵便の宛先		Post office address	